

STUCCOCRYL™

STUCCOCRYL™

STUCCOCRYL admixture is an acrylic-based Portland Cement Plaster modifier designed to improve the mechanical properties and adhesion of the cement mix.

Recommended Use

STUCCOCRYL is used in exterior or interior applications. Portland cement mixes with STUCCOCRYL are fast curing and durable, and exhibit improved tensile and flexural strength compared to mixes made with plain water.

Reduction

Suggested STUCCOCRYL to clean water ratios:

Portland Cement Plaster	1:3
Bonding Slurry	1:2
Key Coat	1:2

VOC Compliance: STUCCOCRYL complies with all known regulations limiting the Volatile Organic Compound (VOC) content of architectural coatings and sealers.

Packaging (5 gallon bucket)
36 lbs. per bucket net
38.8 lbs. per bucket gross

Application

Surface Preparation

Surfaces to receive STUCCOCRYL-modified Portland Cement Plaster must be clean, dry and free of dust, dirt, grease, efflorescence, mildew, release agents or loose material. Bonding strength relies on a structurally sound and clean surface.

Application Procedures

Mix sand and Portland cement thoroughly. Mix STUCCOCRYL with clean water. Add to the dry mix of concrete. Do not over mix.

Clean-Up

Clean with water while STUCCOCRYL is still wet.

Storage

Store STUCCOCRYL in its original containers at temperatures not less than 40°F (4°C) or greater than 110°F (43°C). Store out of direct sunlight. Do not stack buckets more than 3 high.

Shelf Life

Approximately 1 year if properly stored.

Limitations

Substrates must be sound, clean, dry and free of dust, dirt, grease or loose material. Surface, air and material temperatures should be minimum 40°F and maximum 100°F during application and for a period of 24 hours after installation. STUCCOCRYL may not be compatible with glazings or other solvent based products. STUCCOCRYL should not be used in areas subject to immersion. Use in well ventilated areas. Protect all adjacent surfaces (door frames, windows, etc.) adequately. The minimum required slope of surfaces to receive application of STUCCOCRYL is 6" of rise in any 12" of horizontal projection. STUCCOCRYL shall not be applied to inclined areas defined as roof.

Safety

ALWAYS WEAR APPROPRIATE EYE AND SKIN PROTECTION WHEN USING THIS PRODUCT. HARMFUL IF SWALLOWED. BEFORE APPLYING THE PRODUCTS REFER TO THE COMPLETE LONG FORM SPECIFICATIONS OF THE Corev AMERICA PRECOR EIFS SYSTEM.

Information contained in this bulletin conforms to the standard detail recommendations and specifications for the installation of Corev products, is presented in good faith, and is applicable as of the date of this document. Corev assumes no liability, expressed or implied, as to the architecture, engineering, or workmanship of any project.